

U. S. Application No. 10/717,264  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

RECEIVED  
CENTRAL FAX CENTER  
JAN 09 2007

### AMENDMENTS TO THE CLAIMS

This listing of the claims will replace all prior versions and listings of claims in the application:

#### Listing of Claims:

1. (Withdrawn) A process of preparing a polymer composition that includes a branched crystalline diene-modified polypropylene random terpolymer, comprising:  
contacting a metallocene catalyst compound with a polymerization medium that includes at least a propylene monomer, a first diene monomer, and a second diene monomer, in which the first diene monomer and the second diene monomer are different non-conjugated dienes, each having 5 or more carbon atoms; and  
conducting polymerization of the monomers in the presence of the metallocene catalyst compound for a time sufficient to provide a branched crystalline diene-modified polypropylene random terpolymer that includes monomeric units derived from each of the monomers, and having from 0.0 wt% to 2.0 wt% ethylene and a heat of fusion of 30 J/g or more.
2. (Withdrawn) A process of preparing a polymer composition that includes a branched crystalline diene-modified polypropylene random terpolymer, comprising:  
contacting a metallocene catalyst compound with a polymerization medium that includes at least a propylene monomer, an  $\alpha$ , internal non-conjugated diene monomer, and a  $\alpha$ ,  $\omega$  non-conjugated diene monomer; and  
conducting polymerization of the monomers in the presence of the metallocene catalyst compound for a time sufficient to provide a branched crystalline diene-modified polypropylene random terpolymer that includes monomeric units derived from each of the monomers, and having from 0.0 wt% to 2.0 wt% ethylene and a heat of fusion of 30 J/g or more.
3. (Withdrawn) The process of claim 1, in which the first diene monomer is an  $\alpha$ , internal diene.
4. (Withdrawn) The process of claim 1, in which the second diene monomer is an  $\alpha$ ,  $\omega$  diene.
5. (Withdrawn) The process of claim 1, in which the first diene monomer is an  $\alpha$ , internal non-conjugated diene monomer; and the second diene monomer is an  $\alpha$ ,  $\omega$  non-conjugated diene monomer.


U. S. Application No. 10/717,26  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

6. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer has an internal double bond comprising a di-substituted vinyl group or a tri-substituted vinyl group.
7. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer has an internal double bond comprising a di-substituted vinyl group or a tri-substituted vinyl group having one or more methyl group substituents.
8. (Withdrawn) The process of claim 1, on which the first diene monomer is an  $\alpha$ , internal non-conjugated diene monomer having an internal double bond comprising a tri-substituted vinyl group having two methyl group substituents.
9. (Withdrawn) The process of claim 1, in which the second diene monomer is an  $\alpha$ ,  $\omega$  diene comprising unsubstituted 1,4-pentadiene; 1,5-hexadiene; 1,6-heptadiene; 1,7-octadiene; 1,8-nonadiene; or 1,9-decadiene.
10. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer comprising substituted 1,4-pentadiene; 1,5-hexadiene; 1,6-heptadiene; 1,7-octadiene; 1,8-nonadiene; or 1,9-decadiene.
11. (Withdrawn) The process of claim 1, in which the second diene monomer comprises 2-methyl-1,5-hexadiene.
12. (Withdrawn) The process of claim 1, in which the first diene monomer comprises 2-methyl-1,5-hexadiene or 7-methyl-1,6-octadiene.
13. (Withdrawn) The process of claim 1, in which the amount of the first diene monomer is greater than the amount of the second diene monomer.
14. (Withdrawn) The process of claim 1, in which the first diene monomer is an  $\alpha$ , internal non-conjugated diene monomer; the second diene monomer is an  $\alpha$ ,  $\omega$  non-conjugated diene monomer; and the amount of the first diene monomer is greater than the amount of the second diene monomer.
15. (Withdrawn) The process of claim 1, in which the polymerization medium includes 50 mol% or more propylene monomers, 10 mol% or less  $\alpha$ , internal non-conjugated diene monomers, and 1 mol% or less  $\alpha$ ,  $\omega$  non-conjugated diene monomers.
16. (Withdrawn) The process of claim 1, in which the metallocene catalyst compound is or includes a substituted or unsubstituted silyl-bridged or ethylene-bridged bis-indenyl metallocene.

U. S. Application No. 10/717,26  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

17. (Withdrawn) The process of claim 1, in which the metallocene compound comprises a bridged metallocene compound having at least two indenyl rings or derivatives of indenyl rings, each ring being substituted at the 2 position.
18. (Withdrawn) The process of claim 1, in which the metallocene compound comprises a bridged metallocene compound having at least two indenyl rings or derivatives of indenyl rings, each ring being substituted at the 2 and 4 positions.
19. (Withdrawn) The process of claim 1, in which the metallocene compound comprises supported dimethylsilylbis(2-methyl-4-phenyl-1-indenyl)zirconium dimethyl.
20. (Withdrawn) The process of claim 1, in which the metallocene includes a dimethylanilinium tetrakis (perfluorophyl) boron activator.
21. (Withdrawn currently amended) The process of claim 1, in which the supported metallocene includes a methylaluminoxane ~~methlyaluminoxane~~ activator.
22. (Withdrawn - currently amended) The process of claim 1, in which the metallocene compound is represented by the formula:

U. S. Application No. 10/717,264  
 Attorney Docket No. 2002B171/2  
 Reply to Office Action of July 14, 2006  
 Amendment dated October 10, 2006



wherein:

M1 is selected from the group consisting of titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R1 and R2 are identical or different, and are one of a hydrogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group, a C<sub>1</sub>-C<sub>10</sub> alkoxy group, a C<sub>6</sub>-C<sub>10</sub> aryl group, a C<sub>6</sub>-C<sub>10</sub> aryloxy group, a C<sub>2</sub>-C<sub>10</sub> alkenyl group, a C<sub>2</sub>-C<sub>40</sub> alkenyl group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, an OH group or a halogen atom; R<sup>1</sup> and R<sup>2</sup> may also be joined together to form an alkanediyl group or a conjugated C<sub>4</sub>-C<sub>40</sub> diene ligand which is coordinated to M<sup>1</sup> in a metallocyclopentene fashion; R<sup>1</sup> and R<sup>2</sup> may also be identical or different conjugated dienes, optionally substituted with one or more hydrocarbyl, tri(hydrocarbyl)silyl groups or hydrocarbyl, tri(hydrocarbyl)silylhydrocarbyl groups, said dienes having up to 30 atoms not counting hydrogen and forming a  $\pi$  complex with M, examples include 1,4-diphenyl-1,3-butadiene, 1,3-pentadiene, 2-methyl-1,3-pentadiene, 2,4-hexadiene, 1-phenyl-1,3-pentadiene, 1,4-dibenzyl-1,3-butadiene, 1,4-ditolyl-1,3-butadiene, 1,4-bis(trimethylsilyl)-1,3-butadiene, and 1,4-dinaphthyl-1,3-butadiene;


Each R<sup>3</sup> is identical or different from the other R<sup>3</sup> and is each a hydrogen atom, a halogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group which may be halogenated, a C<sub>6</sub>-C<sub>10</sub> aryl group which may be halogenated, a C<sub>2</sub>-C<sub>10</sub> alkenyl group, a C<sub>7</sub>-C<sub>40</sub> -arylalkyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl

U. S. Application No. 10/717,266  
 Attorney Docket No. 2002B171/2  
 Reply to Office Action of July 14, 2006  
 Amendment dated October 10, 2006

group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, a -NR'<sup>2</sup>, -SR', -OR', -OSiR'<sup>3</sup> or -PR'<sup>2</sup> radical, wherein R' is one of a halogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group, or a C<sub>6</sub>-C<sub>10</sub> aryl group;

R<sup>4</sup> to R<sup>7</sup> are identical or different and are hydrogen, or are as defined for R<sup>3</sup> or two or more adjacent radicals R<sup>5</sup> to R<sup>7</sup> together with the atoms connecting them form one or more rings;

R<sup>13</sup> is




-B(R<sup>14</sup>)-, -Al(R<sup>14</sup>)-, -Ge-, -Sn-, -O-, -S-, -SO-, -SO<sub>2</sub>-, -N(R<sup>14</sup>)-, -CO-, -P(R<sup>14</sup>)-, or -P(O)(R<sup>14</sup>)-;

wherein: R<sup>14</sup>, R<sup>15</sup> and R<sup>16</sup> are identical or different and are a hydrogen atom, a halogen atom, a C<sub>1</sub>-C<sub>20</sub> branched or linear alkyl group, a C<sub>1</sub>-C<sub>20</sub> fluoroalkyl or silaalkyl group, a C<sub>6</sub>-C<sub>30</sub> aryl group, a C<sub>6</sub>-C<sub>30</sub> fluoroaryl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a C<sub>2</sub>-C<sub>20</sub> alkenyl group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl group, or R<sup>14</sup> and R<sup>15</sup>, together with the atoms binding them, form a cyclic ring;

or, R<sup>13</sup> is represented by the formula:

U. S. Application No. 10/717,211  
 Attorney Docket No. 2002B171/2  
 Reply to Office Action of July 14, 2006  
 Amendment dated October 10, 2006




wherein:  $R^{17}$  to  $R^{24}$  are as defined for  $R^1$  and  $R^2$ , or two or more adjacent radicals  $R^{17}$  to  $R^{24}$ , including  $R^{20}$  and  $R^{21}$ , together with the atoms connecting them form one or more rings;

$M^2$  is one or more carbons, silicon, germanium or tin; and

$R^8$ ,  $R^9$ ,  $R^{10}$ ,  $R^{11}$  and  $R^{12}$  are identical or different and have the meanings stated for  $R^4$  to  $R^7$ .

23. (Withdrawn - currently amended) The process of claim 1, in which the metallocene compound is represented by the formula:

U. S. Application No. 10/717,26  
 Attorney Docket No. 2002B171/2  
 Reply to Office Action of July 14, 2006  
 Amendment dated October 10, 2006



wherein: M is a metal of Group 4, 5, or 6 of the Periodic Table, for example titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten, preferably, zirconium, hafnium and titanium, most preferably zirconium and hafnium;

$R^1$  and  $R^2$  are identical or different, and are one of a hydrogen atom, a  $C_1$ - $C_{10}$  alkyl group, a  $C_1$ - $C_{10}$  alkoxy group, a  $C_6$ - $C_{10}$  aryl group, a  $C_6$ - $C_{10}$  aryloxy group, a  $C_2$ - $C_{10}$  alkenyl group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_8$ - $C_{40}$  arylalkenyl group, or a halogen atom, or a conjugated diene which is optionally substituted with one or more hydrocarbyl, tri(hydrocarbyl)silyl groups or hydrocarbyl, tri(hydrocarbyl)silylhydrocarbyl groups, said diene having up to 30 atoms not counting hydrogen;



$R^3$  and  $R^4$  are defined the same as are  $R^1$  and  $R^2$ ;

$R^5$  and  $R^6$  are identical or different, and are one of a hydrogen atom, a halogen atom, a  $C_1$ - $C_{10}$  alkyl group, which may be halogenated, a  $C_6$ - $C_{10}$  aryl group, which may be halogenated, a  $C_2$ - $C_{10}$  alkenyl group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_8$ - $C_{40}$  arylalkenyl group, a  $[-NR_2^{15}]$ ,  $-NR_2^{15}$ ,  $[-SR^{15}]$ ,  $-SR^{15}$ ,  $[-OR^{15}]$ ,  $-OR^{15}$ ,

U. S. Application No. 10/717,200  
 Attorney Docket No. 2002B171/Z  
 Reply to Office Action of July 14, 2006  
 Amendment dated October 10, 2006

$[[\text{-OSiR}^3_{15}]] \text{-OSiR}^3_{15}$  or  $[[\text{-PR}^2_{15}]] \text{-PR}^2_{15}$  radical, wherein:  $[[\text{R}^{15}]] \text{R}^3$  is one of a halogen atom, a  $\text{C}_1\text{-C}_{10}$  alkyl group, or a  $\text{C}_6\text{-C}_{10}$  aryl group;

$\text{R}^7$  is



$\text{-B(R}^{14}\text{)-}$ ,  $\text{-Al(R}^{14}\text{)-}$ ,  $\text{-Ge-}$ ,  $\text{-Sn-}$ ,  $\text{-O-}$ ,  $\text{-S-}$ ,  $\text{-SO-}$ ,  $\text{-SO}_2\text{-}$ ,  $\text{-N(R}^{14}\text{)-}$ ,  $\text{-CO-}$ ,  $\text{-P(R}^{14}\text{)-}$ , or  $\text{-P(O)(R}^{14}\text{)-}$ ;

wherein:  $\text{R}^{14}$ ,  $\text{R}^{15}$  and  $\text{R}^{16}$  are identical or different and are a hydrogen atom, a halogen atom, a  $\text{C}_1\text{-C}_{20}$  branched or linear alkyl group, a  $\text{C}_1\text{-C}_{20}$  fluoroalkyl or silaalkyl group, a  $\text{C}_6\text{-C}_{30}$  aryl group, a  $\text{C}_6\text{-C}_{30}$  fluoroaryl group, a  $\text{C}_1\text{-C}_{20}$  alkoxy group, a  $\text{C}_2\text{-C}_{20}$  alkenyl group, a  $\text{C}_7\text{-C}_{40}$  arylalkyl group, a  $\text{C}_8\text{-C}_{40}$  arylalkenyl group, a  $\text{C}_7\text{-C}_{40}$  alkylaryl group, or  $\text{R}^{14}$  and  $\text{R}^{15}$ , together with the atoms binding them, form a cyclic ring;

$\text{M}^2$  is carbon, silicon, germanium or tin;

$\text{R}^8$  and  $\text{R}^9$  are  $\text{R}^8$  and  $\text{R}^9$ , are identical or different, and have the meanings stated for  $\text{R}^5$  and  $\text{R}^6$ ;

$\text{R}^{10}$ ,  $\text{R}^{11}$ ,  $\text{R}^{12}$  and  $\text{R}^{13}$  are identical or different and have the meanings stated for  $\text{R}^5$  and  $\text{R}^6$ ; wherein at least one of  $\text{R}^{13}$  and  $\text{R}^{10}$  are identical or different, and are one of a hydrogen atom, a halogen atom, a  $\text{C}_1\text{-C}_{10}$  alkyl group, which may be halogenated, a  $\text{C}_6\text{-C}_{10}$  aryl group, which may be halogenated, a  $\text{C}_2\text{-C}_{10}$  alkenyl group, a  $\text{C}_7\text{-C}_{40}$  arylalkyl group, a  $\text{C}_7\text{-C}_{40}$  alkylaryl group, a  $\text{C}_8\text{-C}_{40}$  arylalkenyl group, a  $[[\text{-NR}^{15}_2]] \text{-NR}^{15}_2$ ,  $[[\text{-SR}^{15}]] \text{-SR}^{15}$ ,  $[[\text{-OR}^{15}]] \text{-OR}^{15}$ ,  $[[\text{-OSiR}^3_{15}]] \text{-OSiR}^3_{15}$  or  $[[\text{-PR}^2_{15}]] \text{-PR}^2_{15}$  radical, wherein:  $[[\text{R}^{15}]] \text{R}^{15}$  is one of a halogen atom, a  $\text{C}_1\text{-C}_{10}$  alkyl group, or a  $\text{C}_6\text{-C}_{10}$  aryl group; and



U. S. Application No. 10/717,264  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

m and n are identical or different and are zero[,] or 1 or 2, m plus n is zero, 1 or 2.

24. (Withdrawn) The process of claim 1, in which the polymerization medium is substantially gel-free following formation of the polypropylene terpolymer.
25. (Withdrawn) The process of claim 1, further comprising crosslinking the polypropylene terpolymer.
26. (Withdrawn) The process of claim 1, in which polymerization medium has less than 90 volume percent diluent.
27. (Withdrawn) The process of claim 1, in which polymerization medium has less than 50 volume percent diluent.
28. (Withdrawn) The process of claim 1, in which polymerization medium has less than 30 volume percent diluent.
29. (Withdrawn) The process of claim 1, in which the final crystalline polypropylene terpolymer is isotactic or syndiotactic.
30. (Withdrawn) The process of claim 1, in which the metallocene catalyst compound is combined with the monomers in the absence of hydrogen or in the presence of hydrogen in an amount of up to 1.0 mole% hydrogen in the reactor.
31. (Withdrawn) The process of claim 1, in which the heat of fusion of the crystalline polypropylene is 50 J/g or more.
32. (Withdrawn currently amended) The process of claim 1, in which the heat of fusion of the branched crystalline polypropylene is 70 J/g or more. ~~Add 75 j/g more~~
33. (Withdrawn) The process of claim 1, in which the heat of fusion of the branched crystalline polypropylene is 100 J/g or more.
34. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.98 or less.
35. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.95 or less.

U. S. Application No. 10/717,261  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

36. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.90 or less.
37. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.80 or less.
38. (Currently amended) A polymer composition that includes a branched crystalline diene-modified polypropylene random terpolymer having propylene units; first diene units; second diene units; from 0.0 wt% to 2.0 wt% ethylene units; and a heat of fusion of 30 J/g or more, wherein the first diene units are derived from 2-methyl-1,5-hexadiene monomer or  $\alpha$ , internal nonconjugated diene monomers and the second diene units are derived from ~~different  $\alpha$ ,  $\omega$~~  non-conjugated diene monomers, each having 5 or more carbon atoms.
39. (Original) The polymer composition of claim 38, in which the random polypropylene terpolymer comprises at least 30% and no more than 95% propylene units; at least 5% and no more than 65% first diene units; at least 0.001% and no more than 2.00% second diene units; and from 0.0 mol% to 3.0 mol% ethylene units.
40. (Currently amended) The polymer composition of claim 38, in which the ~~first diene units are derived from  $\alpha$ , internal non-conjugated diene monomers~~ branched crystalline polypropylene has a Branching Index of 0.95 or less.
41. (Currently amended) The polymer composition of claim 38, in which the ~~second diene units are derived from  $\alpha$ ,  $\omega$  non-conjugated diene monomers~~ branched crystalline polypropylene has a Branching Index of 0.90 or less.
42. (Currently amended) The polymer composition of claim 38, in which the first diene ~~monomer is an  $\alpha$ , internal non-conjugated diene monomer that is~~ units are present in the polypropylene terpolymer in an amount of from 0.0005 mol% to 10 mol%.
43. (Currently amended) The polymer composition of claim 38, in which the first diene ~~monomer is an  $\alpha$ , internal non-conjugated diene monomer that is~~ units are present in the polypropylene terpolymer in an amount of from 0.005 mol% to 1 mol%.
44. (Currently amended) The polymer composition of claim 38, in which the first diene ~~monomer is an  $\alpha$ , internal non-conjugated diene monomer selected from the group consisting of 2-methyl-1,5-hexadiene and~~ units are derived from 7-methyl-1, 6-octadiene.
45. (Original) The polymer composition of claim 38, in which the branched final crystalline polypropylene has a crystallization temperature ( $T_c$ ) of 50°C or more.

U. S. Application No. 10/717,212  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

46. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of 75°C or more.
47. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of 100°C or more.
48. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of 110°C or more.
49. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of from 50°C to 115°C.
50. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of 75°C or more.
51. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of 100°C or more.
52. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of 125°C or more.
53. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of 150°C or more.
54. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of 160 °C or more.
55. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Tm) of from 75°C to 160°C.
56. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.01 or more.
57. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.1 or more.
58. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.5 or more.

U. S. Application No. 10/717,26  
Attorney Docket No. 2002B171/2  
Reply to Office Action of July 14, 2006  
Amendment dated October 10, 2006

59. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.7 or more.
60. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 1.0 or more.
61. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 1.5 or more.